ACIMENTEIRADOLOURO


PRODUCT TECHNICAL DATA SHEET


CE

Marmocim Revolution - Natural


units: mm

Photo and Dimensions of the Piece





Step: Available in all models
Skirting: Available in all models
Application: Floorings and Facades



N 435 Mono | N 459 Winter | N 456 Contrast | N 451 Platinum | N 443 Dawn | N 457 Silver | N 458 Void | N 447 Moon

N 444 Stardust | N 454 Night | N 452 Graphite | N 445 White | N 440 Ivory | N 441 Memory | N 448 Tale | N 450 Summer

N 455 Pepper | N 453 Mars | N 442 Dune | N 449 Dusk | N 446 Song | N 419 Jungle | N 420 Botanic

Product Features and Palletization

Dimensions (Length x width x thickness)	410 x 410 x 18
Items/Pallet	178 units
Items/sqm	5,95 units
sqm/Item	0,168 sqm
sqm/Pallet	30 sqm
Average weight/sqm	42 kg
Average weight/Item	7,3 kg
Average weight/Pallet	1300 kg

Technical Specifications

EN 1339 – "Concrete paving flags – Requirements and test methods"

Intended use		**Internal Flooring**	**External Flooring**
Emission of asbestos		Approved	Not Relevant
Breaking Strength (MPa)		≥ 5	≥ 5
Slip/ Skid Resistance	**EN 1339**	Satisfactory	Satisfactory
	DIN 51130	R10	R10
	DIN 51097	Class A	Class A
Thermal Conductivity [W/(mk)]		1,24	Not Relevant
External fire performance		Not Relevant	Not Relevant
Durability		Satisfactory	Satisfactory
Reaction to fire		Class A1	Not Relevant

Approved:	**Elaborate:**	**PTDS nº:**	**Date:**
Vítor Silva	Joana Ferreira	MARM_010_EN	22-04-2025

A Cimenteira do Louro, S.A. | Ap. 163 E.C. Famalicão
4761-926 V.N. Famalicão, Portugal
www.aclweb.pt
acl@aclweb.pt

Given the characteristics of aggregates and their photographic reproduction, there may be slight variations in particle size and tone.